

# Datasheet

## Description

Conc. red., DIN2616/EN10253-2-B  
P235GH, certificate 3.1

## Main data

406.40 x 10.00 / 323.90 x 10.00

D	406.40 mm
S1	10.00 mm
d	323.90 mm
S2	10.00 mm
L	355.00 mm



## Chemical analysis (heat) in % of mass

(one content=max. value)

Short name: P235GH

Mat. grade: 1.0345

C	Si	Mn	P	S	Cr	Cu	Mo	Nb	Ni	Ti	V	Others
0.16	0.35	1.20	0.025	0.020	0.30	0.30	0.08	0.01	0.30	0.04	0.02	Al

## Mechanical properties

Short name: P235GH

Mat. grade: 1.0345

Upper yield strength $reH$ or $Rp0.2$ min for wallthicknesses $T$ in mm, N/mm <sup>2</sup> at room temperature		Tensile strength $Rm$ for wallthickn. $T$ in mm, N/mm <sup>2</sup> at room temperature		Elongation $A$ at room- temperature, min.%		Min. impact energy KV in J	
$T \leq 16$	$16 < T \leq 60$	$T \leq 16$	$16 < T \leq 60$	Longit.	Transv.	Longit.	Transv.
235	225	360-500	360-500	25	23	40	27

Sources: EN 10253, DIN 17175, DIN 2528, DIN 1629, Stahlschlüssel, ASTM