

Datasheet

Description

Conc. red., DIN2616/EN10253-1
ST37.0, certificate ohne

Main data

193.70 x 5.60 / 159.00 x 4.50

D	193.70 mm
S1	5.60 mm
d	159.00 mm
S2	4.50 mm
L	152.00 mm



Chemical analysis (heat) in % of mass

(one content=max. value)

Short name: ST37.0

Mat. grade: 1.0254

C	Si	Mn	P	S	Cr	Cu	Mo	Nb	Ni	Ti	V	Others
0.16	0.35	1.20	0.025	0.020	0.30	0.30	0.08	0.01	0.30	0.04	0.02	

Mechanical properties

Short name: ST37.0

Mat. grade: 1.0254

Upper yield strength reH or Rp0.2 min for wallthicknesses T in mm, N/mm2 at room temperature		Tensile strength Rm for wallthickn. T in mm, N/mm2 at room temperature		Elongation A at room- temperature, min.%		Min. impact energy KV in J	
T<=16	16<T<=60	T<=16	16<T<=60	Longit.	Transv.	Longit.	Transv.
235	225	350-480	350-480	25	23		

Sources: EN 10253, DIN 17175, DIN 2528, DIN 1629, Stahlschlüssel, ASTM