

Datasheet

Description

Conc. red., DIN2616/EN10253-1
ST37.0, certificate ohne

Main data

114.30 x 13.00 / 88.90 x 13.00

D	114.30 mm
S1	13.00 mm
d	88.90 mm
S2	13.00 mm
L	100.00 mm



Chemical analysis (heat) in % of mass

(one content=max. value)

Short name: ST37.0

Mat. grade: 1.0254

C	Si	Mn	P	S	Cr	Cu	Mo	Nb	Ni	Ti	V	Others
0.16	0.35	1.20	0.025	0.020	0.30	0.30	0.08	0.01	0.30	0.04	0.02	

Mechanical properties

Short name: ST37.0

Mat. grade: 1.0254

Upper yield strength reH or Rp0.2 min for wallthicknesses T in mm, N/mm2 at room temperature		Tensile strength Rm for wallthickn. T in mm, N/mm2 at room temperature		Elongation A at room- temperature, min.%		Min. impact energy KV in J	
T<=16	16<T<=60	T<=16	16<T<=60	Longit.	Transv.	Longit.	Transv.
235	225	350-480	350-480	25	23		

Sources: EN 10253, DIN 17175, DIN 2528, DIN 1629, Stahlschlüssel, ASTM