

Datasheet


Description

Elbows, DIN2605/EN10253-2-A-5D-90°
P355NH, certificate 3.1

Main data

Type 5 , 90°, 60.30 x 4.50 mm

D	60.30 mm
S	4.50 mm
r	137.50 mm



Chemical analysis (heat) in % of mass

(one content=max. value)

Short name: P355NH

Mat. grade: 1.0565

C	Si	Mn	P	S	Cr	Cu	Mo	Nb	Ni	Ti	V	Others
0.18	0.50	1.70	0.025	0.010	0.30	0.30	0.08	0.05	0.50	0.03	0.10	Al. N

Mechanical properties

Short name: P355NH

Mat. grade: 1.0565

Upper yield strength reH or Rp0.2 min for wallthicknesses T in mm, N/mm2 at room temperature		Tensile strength Rm for wallthickn. T in mm, N/mm2 at room temperature		Elongation A at room- temperature, min.%		Min. impact energy KV in J	
T<=16	16<T<=60	T<=16	16<T<=60	Longit.	Transv.	Longit.	Transv.
355	345	490-650	490-630	22	20	55	39

Sources: EN 10253, DIN 17175, DIN 2528, DIN 1629, Stahlschlüssel, ASTM