protubo.biz
passt einfach perfekt

Datasheet

team@protubo.biz
T +49 (0) 4202 95 55 50


Description


Welding nippel, EN10241, TAB 22,
conical thread, S235W, cert. 2.2

Main data

1/2" x 50 mm

d1	1/2"
L	50 mm





Chemical analysis (heat) in % of mass

(one content=max. value)

Short name: S235W

Mat. grade: 1.0037

C	Si	Mn	P	S	Cr	Cu	Mo	Nb	Ni	Ti	V	Others
0.17		1.40	0.045	0.045								N

Mechanical properties

Short name: S235W

Mat. grade: 1.0037

Upper yield strength reH or Rp0.2 min for wallthicknesses T in mm, N/mm2 at room temperature		Tensile strength Rm for wallthickn. T in mm, N/mm2 at room temperature		Elongation A at room-temperature, min.%		Min. impact energy KV in J	
T<=16	16<T<=60	T<=16	16<T<=60	Longit.	Transv.	Longit.	Transv.
235	225	360-500	360-500	25	25		

Sources: EN 10253, DIN 17175, DIN 2528, DIN 1629, Stahlschlüssel, ASTM

protubo.biz is a registered trademark of PM Fittings GmbH. Information without guarantee. Errors and omissions excepted